

	Pin #1	Pin #2	Pin #3	Pin #4
Power density at EOI (W/cc)	412	542	492	364
Burn-up at EOI (at%)	1.14	1.57	1.53	1.11
Temperature (°C)	990	1370	1180	980

Table 6 : Average power density, burn-up and temperature at end of irradiation (EOI) for each mini-pin.